

1. Material Substrate GaAs (N Type)
Epitaxial Layer GaAs (P/N Type)

2. Electrode N(Cathode) Side Gold Alloy
P(Anode) Side Gold Alloy


3. Electro-Optical Characteristics

Parameter	Symbol	Min	Typ	Max	Unit	Condition
Forward Voltage	V_F			1.6	V	IF=100mA
Reverse Voltage	V_R	8			V	IR=10uA
Power	P_O	0.479	0.62		mW	IF=50mA
Wavelength	λ_P		940		nm	IF=20mA
	$\Delta\lambda$		45		nm	IF=20mA

※ Note : Power is measured by Sorter E/T system with bare chip.

4. Mechanical Data

- (a) Emission Area ----- 13.8mil x 13.8mil
- (b) Bottom Area ----- 14.6mil x 14.6mil
- (c) Bonding Pad ----- 135um
- (d) Chip Thickness ----- 11mil
- (e) Junction Height ----- 8.2mil



AUK Corp.

Eoyang factory, 513-5 Eoyang-dong, Iksan, 570-210, Korea

Tel. +82 63 839 1111 Fax. +82 63 835 8259

www.auk.co.kr

