Higher Performance, High Reliability Insulator

Features and Benefits

- Thermal impedance: 0.38°C-in²/W (@50 psi)
- Optimal heat transfer
- High thermal conductivity: 3.5 W/m-K



Sil-Pad 2000 is a high performance, thermally conductive insulator designed for demanding aerospace and commercial applications.

Sil-Pad 2000 is a silicone elastomer formulated to maximize the thermal and dielectric performance of the filler/binder matrix. The result is a grease-free, conformable material capable of meeting or exceeding the thermal and electrical requirements of high-reliability electronic packaging applications.

TYPICAL PROPERTIES OF SIL-PAD 2000						
PROPERTY	IMPERIAL VALUE		METRIC VALUE		TEST METHOD	
Color	White		White		Visual	
Reinforcement Carrier	Fiberglass		Fiberglass			
Thickness (inch) / (mm)	0.010 to 0.020		0.254 to 0.508		ASTM D374	
Hardness (Shore A)	90		90		ASTM D2240	
Continuous Use Temp (°F) / (°C)	-76 to 392		-60 to 200			
ELECTRICAL						
Dielectric Breakdown Voltage (Vac)	4000		4000		ASTM D149	
Dielectric Constant (1000 Hz)	4.0		4.0		ASTM D150	
Volume Resistivity (Ohm-meter)	10"		1011		ASTM D257	
Flame Rating	V-O		V-O		U.L.94	
THERMAL						
Thermal Conductivity (W/m-K)	3.5		3.5		ASTM D5470	
THERMAL PERFORMANCE vs PRESSURE						
Press	sure (psi)	10	25	50	100	200
TO-220 Thermal Performance (°C/W)		2.61	2.32	2.02	1.65	1.37
Thermal Impedance (°C-in²/W) (1)		0.57	0.43	0.38	0.35	0.30
I) The ASTM D5470 test fixture was used. The recorded value includes interfacial thermal resistance. These						

values are provided for reference only. Actual application performance is directly related to the surface roughness, flatness and pressure applied

Typical Applications Include:


- Power supplies
- Power semiconductors
- Avionics

- Motor controls
- U.L. File Number E59150
- Aerospace

Configurations Available:

- Sheet form, die-cut parts
- With or without pressure sensitive adhesive

Building a Part Number



Standard Options

4 example

NA = Selected standard option. If not selecting a standard option, insert company name, drawing number, and revision level.

Standard configuration dash number, $1212 = 12" \times 12"$ sheets, or 00 = custom configuration

AC = Adhesive, one side 00 = No adhesive

Standard thicknesses available: 0.010", 0.015", 0.020"

SP2000 = Sil-Pad 2000 Material

Note: To build a part number, visit our website at www.bergquistcompany.com.

Sil-Pad®: U.S. Patents 4,574,879; 4,602,125; 4,602,678; 4,685,987; 4,842,911 and others



18930 West 78th Street Chanhassen, MN 55317 Phone: 800-347-4572 Fax: 952-835-0430

www.bergquistcompany.com The Bergquist Company -European Headquarters

The Bergquist Company - Asia Room 15, 8/F Wah Wai Industrial Centre No. 38-40, Au Pui Wan Street Bramenberg 9a, 3755 BT Eemnes Netherlands Phone: 31-35-5380684 Fax: 31-35-5380295 Fotan, Shatin, N.T. Hong Kong Ph: 852.2690.9296 Fax: 852.2690.2344

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NOTHER SELLER NOR MANUFACTURER SHALL BE LIABLE ETHER INTORY TO RIN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INANY LOST OF A DOUBLICE THE USE OR THE INTORY TO REVENUE ARISING OUT OF THE USE OR THE INANY LOST OF ADDITION THE USE OR THE INTORY TO REVENUE ARISING OUT OF THE USE OR THE INANY LOST OF ADDITION THE USE OR THE INTORY TO REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacture.