

Dielectric Powders

Disk Type – Wet Extrusion Processes

Product Features

- Three Categories of Products:
 - 1. Temperature Compensation Type
 - 2. High-K Type
 - 3. Semi-Conductive Type



Temperature Compensation Type

| Designation | Electric Properties | | | Reference Code | | Reference Firing Temperature, °C |
|-------------|---------------------|---------------|-----------------|----------------|-----|----------------------------------|
| | K-value at 1MHz | Q Factor Min. | I.R. Min. MΩ | JIS | EIA | |
| NPO-10 | 10.0±1.0 | 2000 | 10 ⁵ | CH | COH | 1320±10 |
| NPO-13 | 13.0±1.0 | 3000 | 10 ⁵ | CG | COG | 1330±10 |
| NPO-20 | 23.0±1.0 | 3000 | 10 ⁵ | CG | COG | 1330±10 |
| NPO-40 | 44.0±1.5 | 3000 | 10 ⁵ | CG | COG | 1210±10 |
| NPO-110 | 107±3 | 3000 | 10 ⁵ | CG | COG | 1270±10 |
| N750 | 100±15 | 2000 | 10 ⁵ | UH | U2H | 1230±10 |
| SL-330 | 325±15 | 2000 | 10 ⁵ | SL | - | 1355±10 |

Contact Us!

Toll Free: 800-929-9888

frontiersales@frontierusa.com

Visit Our Website!
www.frontierUSA.com



Dielectric Powders

Disk Type – Wet Extrusion Processes

High-K Type

| Designation | Electric Properties | | | Reference Code | | Reference Firing Temperature, °C |
|-------------|---------------------|------------|-----------------|----------------|-----|----------------------------------|
| | K-value at 25°C | D.F. Max.% | I.R. Min MΩ | JIS | EIA | |
| Z5U | 11500±1500 | 1 | 10 ⁴ | ZE | Z5U | 1360±10 |
| Z5V | 20000±3000 | 1 | 10 ⁴ | ZF | Z5V | 1380±10 |
| Y5U | 8500±850 | 1 | 10 ⁴ | YE | Y5U | 1330±10 |
| Y5E | 1710±100 | 1 | 10 ⁴ | YA | Y5E | 1255±10 |
| Y5P | 3650±200 | 1.5 | 10 ⁴ | YB | Y5P | 1390±10 |
| Y5V | 15500±2000 | 1 | 10 ⁴ | YF | Y5V | 1380±10 |
| Y5P-XHT | 3650±350 | 2.0 | 10 ⁴ | YB | Y5P | 1390±10 |
| X7R | 3300±330 | 2.0 | 10 ⁴ | | X7R | 1355±10 |

Semi-conductive Type

| Designation | Electric Properties | | | Reference Code | | Reference Firing Temperature, °C |
|-------------|---------------------|------------|-----------------|----------------|-----|----------------------------------|
| | K-value at 25°C | D.F. Max.% | I.R. Min. MΩ | JIS | EIA | |
| SBL— Y5V | 12000±1000 | 0.45 | 10 ⁴ | YF | Y5V | 1300±10 |
| SBL— Y5U | 8500±500 | 0.5 | 10 ⁴ | YE | Y5U | 1325±10 |

Contact Us!

Toll Free: 800-929-9888

frontiersales@frontierusa.com

Visit Our Website!

www.frontierusa.com

www.fecpowders.com

